

Starbase is produced from high quality recycled rebond polyurethane foam. This lightweight polyurethane foam guarantees a stable and durable installation and increase the experience of luxury and comfort of the carpet. Starbase is suitable for domestic and project applications as entrances, restaurants, corridors, rooms and stairways.

- Excellent compression recovery capability
- Lightweight and easy to install
- Environmental friendly produced and 100% recycled material
- Fire retardant Euroclass Bfl-S1

Installation method :Double stick method or stretched installation - crepe side up.Direction of installation methodAlways install the underlay in a 90° angle underneath the length of the carpet in order to avoid matching of seams in underlay and carpet.Direction of installation methodAlways install the underlay in a 90° angle underneath the length of the carpet in order to avoid matching of seams in underlay and carpet.General building inspection license:Z-158.10-93 valid until 9-5-2023Quietroom® label :Registration no 201782112Thickness:8 mm / ± 0,8 mm - maximum tolerance 10%Dimensions:10m x 1,5m = ± 15m²Weight:1280 gr/m² / ± 128 gr - maximum tolerance 10%Density:160 kg/m³ / ± 16 kg - maximum tolerance 10%Material:Top Layer :crepe Middle Layer :Middle Layer :Rebond polyurethane foam Bottom Layer :Packing:Material :Printed LDPE foil (no core) with insert sheet.			
General building inspection license:       Z-158.10-93 valid until 9-5-2023         Quietroom® label :       Registration no 201782112         Thickness:       8 mm / ± 0,8 mm - maximum tolerance 10%         Dimensions:       10m x 1,5m = ± 15m²         Weight:       1280 gr/m² / ± 128 gr - maximum tolerance 10%         Density:       160 kg/m³ / ± 16 kg - maximum tolerance 10%         Material:       Top Layer :       crepe Middle Layer :         Rebond polypropylene non-woven       Spunbond polypropylene non-woven	Installation method :	Double stick method or stretched installation - crepe side up.	
license:Z-158.10-93 valid until 9-5-2023Quietroom® label :Registration no 201782112Thickness:8 mm / ± 0,8 mm - maximum tolerance 10%Dimensions:10m x 1,5m = ± 15m²Weight:1280 gr/m² / ± 128 gr - maximum tolerance 10%Density:160 kg/m³ / ± 16 kg - maximum tolerance 10%Material:Top Layer :Crepe Middle Layer :Rebond polyurethane foam Bottom Layer :	Direction of installation method		
Quietroom® label :Registration no 201782112Thickness:8 mm / ± 0,8 mm - maximum tolerance 10%Dimensions:10m x 1,5m = ± 15m²Weight:1280 gr/m² / ± 128 gr - maximum tolerance 10%Density:160 kg/m³ / ± 16 kg - maximum tolerance 10%Material:Top Layer :crepe Middle Layer :Rebond polyurethane foam Bottom Layer :Rebond polyurethane foam Spunbond polypropylene non-woven	- · ·		
Thickness: $8 \text{ mm} / \pm 0, 8 \text{ mm} - \text{maximum tolerance 10%}$ Dimensions: $10m \times 1, 5m = \pm 15m^2$ Weight: $1280 \text{ gr/m}^2 / \pm 128 \text{ gr} - \text{maximum tolerance 10%}$ Density: $160 \text{ kg/m}^3 / \pm 16 \text{ kg} - \text{maximum tolerance 10%}$ Material:Top Layer :crepeMiddle Layer :Rebond polyurethane foam Bottom Layer :Spunbond polypropylene non-woven	license:	2-150.10-95 Valid Until 9-5-2025	
Dimensions: $10m \times 1,5m = \pm 15m^2$ Weight: $1280 gr/m^2 / \pm 128 gr - maximum tolerance 10\%$ Density: $160 kg/m^3 / \pm 16 kg - maximum tolerance 10\%$ Material:Top Layer :CrepeMiddle Layer :Rebond polyurethane foam Bottom Layer :Spunbond polypropylene non-woven	Quietroom® label :	Registration no 201782112	
Weight:1280 gr/m² / ± 128 gr - maximum tolerance 10%Density:160 kg/m³ / ± 16 kg - maximum tolerance 10%Material:Top Layer :crepeMiddle Layer :Rebond polyurethane foamBottom Layer :Spunbond polypropylene non-woven	Thickness:	8 mm / ± 0,8 mm - maximum tolerance 10%	
Density:       160 kg/m³ / ± 16 kg - maximum tolerance 10%         Material:       Top Layer :       crepe         Middle Layer :       Rebond polyurethane foam         Bottom Layer :       Spunbond polypropylene non-woven	Dimensions:	$10m \times 1,5m = \pm 15m^2$	
Material:       Top Layer :       crepe         Middle Layer :       Rebond polyurethane foam         Bottom Layer :       Spunbond polypropylene non-woven	Weight:	1280 gr/m <sup>2</sup> / $\pm$ 128 gr - maximum tolerance 10%	
Middle Layer :       Rebond polyurethane foam         Bottom Layer :       Spunbond polypropylene non-woven	Density:	160 kg/m <sup>3</sup> / $\pm$ 16 kg - maximum tolerance 10%	
Packing:     Material :     Printed LDPE foil (no core) with insert sheet.	Material:	Middle Layer :	Rebond polyurethane foam
	Packing:	Material :	Printed LDPE foil (no core) with insert sheet.



Estillon B.V. - t +31 (0)24 648 53 48 - e info@estillon.nl - www.estillon.com

Versie 1.2 29/8/2018

## Technical information:



Dimensional stability Traction	: 40 N/mm <sup>2</sup> /lenght 156N / width 62N
Dimensional stability extension: (test method: ISO 13934-1)	: 10% / lenght 5% / width 3%
<i>Caster chair test</i> (Test method: EN 985)	: Suitable, double stick only
Impact sound reduction (Test method: NA)	: ΔLw = 29 dB
Thermal resistance (Test method: NA)	: 8mm = 2,7 togs - 0,27 m <sup>2</sup> K/W
Fire retardency	: Bfl-S1
(Test methode: EN 13501-1 (2007) + A1 (2013)) ASTM radial panel test	: NA
(Test methode: ASTM E 648-06) Russian requirements on fire safety	: Class KM3
(Test methode: FZ-123)	


## Installation instructions:

• Let the carpet as well as the underpadding acclimatise for 24 hours in the original packing in the room to be installed.

- The best temperature for installation is 5-20°C. and a humidity of 50-70%.
- make sure that the underfloor is absolutely dry and free of grit and dust.
- To cut the underpadding we recommend to use a trapezium blade.
- Underpadding can not prevant the natural shrinkage of carpet. For that reason we strongly advise always to use the double stick method (gluing both the underpadding as well as the carpet) in case of shrink-sensible qualities. Always follow the installation instructions of the carpet Manufacturer.

## Important:

In case the installation has not been done in accordance with the installation instructions, estillon can not be held responsible for any damage or claim as a result of an incorrect installation. In case of doubt always consult your supplier.





Estillon B.V. - t +31 (0)24 648 53 48 - e info@estillon.nl - www.estillon.com

Versie 1.2 29/8/2018