Floorfixx Balance 200 - 62216



Floorfixx Balance 200 is a dry levelling fill (according to DIN 18560-2) made of mineral-coated wood chips. This patented process guarantees the longevity of the product. The grains remain permanently stable, do not crumble and are resistant to mould. The outstanding advantage is the processing without water or binding agents. The fill is stable in position and can be walked on immediately after installation. For use with a floating flat base floor, use Floorfixx Regular (62200) or Floorfixx Comfort (62210) over the granules.

Due to the special grain size distribution, Floorfixx Balance 200 is particularly suitable for levelling hollow spaces or height differences that need to be accommodated. Floorfixx Balance 200 is applied without water or binder and is a quick and inexpensive alternative to wet levelling compounds on concrete-wood floors.

With the large grain - Floorfixx Balance 200 - large irregularities can be absorbed. Finish the top layer with the small grain - Floorfixx Balance 020 - for a nice even end result.

- High quality in terms of building physics
- Insensitive to moisture
- Mould resistant and durable
- VOC free
- Ecologically recyclable

Contents:	50 ltr. / bag	
Grain size:	4,0 - 8,0 mm	
Fill height:	10 - 200 mm	
Weight per unit:	360 gram/m²/mm / Maximum tolerance ± 10%	
Density:	360 kg/m³	
Material requirement:	10 Ltr./m2/cm H.	
Installation Height:	10-200 mm	
Material:	Mineral-coated wood chips	
Packing:		
Contents:	Packaging :	36 bags per pallet
	Contents :	50 ltr. / bag
	Weight :	16 kg. / bag



Estillon B.V. - t +31 (0)24 648 53 48 - e info@estillon.nl - www.estillon.com

Versie 1.0 10-6-20

## Floorfixx Balance 200 - 62216



## Technical data:

Grain compressive strength	: 12,6 N/mm <sup>2</sup>
<i>Castor chair use</i> (Test method: EN 985)	: NA
<i>Impact sound reduction</i> (Test methode: NA)	: NA
<i>Heat resistance</i> (test methode: NA)	: 0,080 W/mK
Floorheating	: Suitable
<i>Flammability</i> (Test method: EN ISO 9239-1)	: B1 / Bfl-S1
<i>Formaldehyde</i> (Test method: EN 120)	: NA

## Installation instruction:



## Important:

If the installation instructions and other instructions are not followed, Estillon cannot be held liable for damages or claims resulting from incorrect installation. In case of doubt, please contact the supplier.





Estillon B.V. - t +31 (0)24 648 53 48 - e info@estillon.nl - www.estillon.com