

LVT MULTI-FIT UNDERLAY

Underlay Technical Specification

Item Code: TALVTMULTIFIT

Issue Date: 19/07/2019

Issue No. 1

Sponge Rubber

Suitable for the installation of luxury vinyl tile flooring






Nominal thickness 1.50 mm EN 823 + Annex A.3.1 Nominal square weight 2500 g/m² (74 oz/yd²) Nominal roll weight 25.00 kg Nominal roll area 10.00 m² (7.30m x 1.37m) Reflected walking sound (RWS) 44 dB DIN EN 16205 Measured under standard LVT Impact sound up to 18 dB EN ISO 10140-3 and ISO 717-2 Measured under standard LVT Thermal resistance 0.12 togs BS 4745 Thermal resistance 0.012 m²k/W EN 12667 or EN 12664 Compressive strength 503 kPa EN 826 + Annex A.3.7 Compressive Creep resistance ≥ 50 kPa EN 1606 + Annex A.3.8 Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball 1800 mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions) Cert. No.0007622	Standard Specifications			
Nominal roll weight25.00 kgNominal roll area10.00 m² (7.30m x 1.37m)Reflected walking sound (RWS)44 dBDIN EN 16205 Measured under standard LVTImpact soundup to 18 dBEN ISO 10140-3 and ISO 717-2 Measured under standard LVTThermal resistance0.12 togsBS 4745Thermal resistance0.012 m²K/WEN 12667 or EN 12664Compressive strength503 kPaEN 826 + Annex A.3.7Compressive Creep resistance≥ 50 kPaEN 1606 + Annex A.3.8Dynamic load resistance>1000,000 cyclesEN 13793 + Annex A.3.9Resistance to impact by large diameter ball1800 mmEN 13329 annex F and EN 438 chapt. 21Punctual Conformability0.55mmEN 16354Hot metal nut test (tested in Interfloor laboratoryLow radius of effects of ignitionBS 4790 & BS 5287Reaction-to-fire (RTF)Bfl-s1BS EN 13501-1 - Table 2(underlay plus flooring in end-use conditions)	Nominal thickness	1.50 mm EN 823 + Annex A.3.1		
Nominal roll area 10.00 m² (7.30m x 1.37m) Reflected walking sound (RWS) 44 dB DIN EN 16205 Measured under standard LVT Impact sound up to 18 dB EN ISO 10140-3 and ISO 717-2 Measured under standard LVT Thermal resistance 0.12 togs BS 4745 Thermal resistance 0.012 m²K/W EN 12667 or EN 12664 Compressive strength 503 kPa EN 826 + Annex A.3.7 Compressive Creep resistance ≥ 50 kPa EN 1606 + Annex A.3.8 Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball Punctual Conformability 0.55mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Nominal square weight	2500 g/m² (74 oz/yd²)		
Reflected walking sound (RWS) 44 dB DIN EN 16205 Measured under standard LVT Impact sound up to 18 dB EN ISO 10140-3 and ISO 717-2 Measured under standard LVT Thermal resistance 0.12 togs BS 4745 Thermal resistance 0.012 m²K/W EN 12667 or EN 12664 Compressive strength 503 kPa EN 826 + Annex A.3.7 Compressive Creep resistance ≥ 50 kPa EN 1606 + Annex A.3.8 Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball 1800 mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Nominal roll weight	25.00 kg		
Impact soundup to 18 dBEN ISO 10140-3 and ISO 717-2 Measured under standard LVTThermal resistance0.12 togsBS 4745Thermal resistance0.012 m²K/WEN 12667 or EN 12664Compressive strength503 kPaEN 826 + Annex A.3.7Compressive Creep resistance≥ 50 kPaEN 1606 + Annex A.3.8Dynamic load resistance>1000,000 cyclesEN 13793 + Annex A.3.9Resistance to impact by large diameter ball1800 mmEN 13329 annex F and EN 438 chapt. 21Punctual Conformability0.55mmEN 16354Hot metal nut test (tested in Interfloor laboratoryLow radius of effects of ignitionBS 4790 & BS 5287Reaction-to-fire (RTF)Bfl-s1BS EN 13501-1 - Table 2(underlay plus flooring in end-use conditions)	Nominal roll area	10.00 m² (7.30m x 1.37m)		
Thermal resistance 0.12 togs BS 4745 Thermal resistance 0.012 m²K/W EN 12667 or EN 12664 Compressive strength 503 kPa EN 826 + Annex A.3.7 Compressive Creep resistance ≥ 50 kPa EN 1606 + Annex A.3.8 Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball 1800 mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Reflected walking sound (RWS)	- 11 - 11 - 11 - 11		
Thermal resistance 0.012 m²K/W EN 12667 or EN 12664 Compressive strength 503 kPa EN 826 + Annex A.3.7 Compressive Creep resistance ≥ 50 kPa EN 1606 + Annex A.3.8 Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball 1800 mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Impact sound	·		
Compressive strength 503 kPa EN 826 + Annex A.3.7 Compressive Creep resistance ≥ 50 kPa EN 1606 + Annex A.3.8 Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball 1800 mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Thermal resistance	0.12 togs BS 4745		
Compressive Creep resistance ≥ 50 kPa EN 1606 + Annex A.3.8 Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball 1800 mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Thermal resistance	0.012 m ² K/W EN 12667 or EN 12664		
Dynamic load resistance >1000,000 cycles EN 13793 + Annex A.3.9 Resistance to impact by large diameter ball 1800 mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Compressive strength	503 kPa EN 826 + Annex A.3.7		
Resistance to impact by large diameter ball Punctual Conformability 0.55mm EN 13329 annex F and EN 438 chapt. 21 Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Compressive Creep resistance	≥ 50 kPa EN 1606 + Annex A.3.8		
Punctual Conformability 0.55mm EN 16354 Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Dynamic load resistance	>1000,000 cycles EN 13793 + Annex A.3.9		
Hot metal nut test (tested in Interfloor laboratory Low radius of effects of ignition BS 4790 & BS 5287 Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Resistance to impact by large diameter ball	1800 mm EN 13329 annex F and EN 438 chapt. 21		
Reaction-to-fire (RTF) Bfl-s1 BS EN 13501-1 - Table 2 (underlay plus flooring in end-use conditions)	Punctual Conformability	0.55mm EN 16354		
(underlay plus flooring in end-use conditions)	Hot metal nut test (tested in Interfloor laboratory	Low radius of effects of ignition BS 4790 & BS 5287		
Russian GOST FR Test Classification M3 Cert. No.0007622		BfI-s1 BS EN 13501-1 - Table 2		
	Russian GOST FR Test	Classification M3 Cert. No.0007622		

Other Specifications

Odour	No objectionable odour
Antimicrobial and mildew resistant	Yes
Colour / backing	Black nonwoven facing / white nonwoven backing
Packaging	Clear, with printed insert

Certificatio





Guarantee

Guaranteed for the serviceable lifetime of the flooring

Notes

* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015





LVT MULTI-FIT UNDERLAY

Underlay Technical Specification

Item Code: TALVTMULTIFIT

Issue Date: 09/07/2019

Issue No. 1



Duralay LVT Underlay is free from plasticisers, asbestos, formaldehyde, halogens and heavy metals.

It complies with the French afsset A+guidelines on VOCs, and meets and the German AgBB scheme standards.

Ecological Aspects

This product is solvent free and does not contain any other ozone depleting substances.

The renewable resources used in the product do not compete with food crops (during growth).



This product does not require any special health and safety measures to be taken. When laying the flooring, it is essential to adhere to the manufacturer's advice on protection.

Processing

The approval of the flooring and adhesive manufacturers must be obtained prior to the installation of the product Please refer to the LVT manufacturer's installation guidelines before fitting

GREEN CREDENTIALS

Green Features	Description	LEED Programme
Recyclable	At the end of the underlays useful life it can be 100% recycled	MR 2.0: Points Available It can be recycled
Recycled Content	Contains not less than 3% pre-consumer recycled material	MR 4.0: Points Available Recycled Content
Indoor Air Quality	Meets or exceeds the industry standard for indoor air quality as established by the CRI Green Label Programme	IEQ 4.3: Points Available Product is Green Label Certifie
Regional Materials	Production Facility Haslingden BB4 4LS, UK Where used within 500 miles of Production Facility	MR 5.0: Points Available

LEED points must be considered along with other building components and must be determined by the specifier/architect or LEED accredited professiona

Certificatio





Guarantee

Guaranteed for the serviceable lifetime of the flooring

Notes

* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015

